



DEECO Metals offers a full range of foundry casting processes for custom metal [castings](#), along with [extrusion](#) and [forging](#) capabilities to support a broad range of metal shapes and custom components. When required, first article samples can be provided for review prior to production. Customers trust [DEECO Metals](#) with critical parts because of our commitment to quality control, consistent manufacturing processes, and reliable performance. From concept through final production, we focus on delivering parts made to your specifications.

METAL GAUGE TO THICKNESS CHART

Values shown as inches (mm)

Gauge	Fraction	Stainless Sheet inches (mm)	Galvanized Steel inches (mm)	Standard Sheet Steel inches (mm)	Aluminum Sheet inches (mm)
26		0.0187 (0.452)	0.0217 (0.55)	0.0179 (0.45)	0.0159 (0.40)
25		0.0219 (0.56)	0.0247 (0.63)	0.0209 (0.53)	0.0179 (0.46)
24		0.0235 (0.5969)	0.0276 (0.70)	0.0239 (0.61)	0.0201 (0.51)
23		0.0281 (0.71)	0.0306 (0.78)	0.0269 (0.68)	0.0226 (0.58)
22	1/32"	0.0293 (0.744)	0.0336 (0.85)	0.0299 (0.76)	0.0253 (0.64)
21		0.0344 (0.86)	0.0366 (0.93)	0.0329 (0.84)	0.0285 (0.71)
20		0.0355 (0.9016)	0.0396 (1.01)	0.0359 (0.91)	0.0320 (0.81)
19		0.0420 (1.067)	0.0456 (1.16)	0.0418 (1.06)	0.0359 (0.91)
18		0.0480 (1.219)	0.0516 (1.31)	0.0478 (1.21)	0.0403 (1.02)
17		0.0562 (1.4)	0.0575 (1.46)	0.0538 (1.37)	0.0453 (1.1)
16	1/16"	0.0595 (1.511)	0.0635 (1.61)	0.0598 (1.52)	0.0508 (1.29)
15		0.0703 (1.8)	0.0710 (1.80)	0.0673 (1.71)	0.0571 (1.4)
14	5/64"	0.0751 (1.9075)	0.0785 (1.99)	0.0747 (1.90)	0.0641 (1.63)
13	3/32"	0.0900 (2.286)	0.0934 (2.37)	0.0897 (2.28)	0.072 (1.8)
12	7/64"	0.1054 (2.677)	0.1084 (2.75)	0.1046 (2.66)	0.0808 (2.05)
11	1/8"	0.1200 (3.048)	0.1233 (3.13)	0.1196 (3.04)	0.0907 (2.30)
10	9/64"	0.1350 (3.429)	0.1382 (3.51)	0.1345 (3.42)	0.1019 (2.59)
9	5/32"	0.1563 (3.97)	0.1532 (3.89)	0.1495 (3.80)	0.1144 (2.91)
8	11/64"	0.165 (4.191)	0.1681 (4.27)	0.1644 (4.18)	0.1285 (3.26)
7	3/16"	0.1874 (4.76)		0.1793 (4.55)	0.1443 (3.67)
6	13/64"	0.2031		0.1943 (4.94)	0.162 (4.1)
5	7/32"	0.2187		0.2092 (5.31)	0.1819
4	15/64"	0.2344		0.2242 (5.69)	0.2043
3	1/4"	0.25		0.2391 (6.07)	0.2294

Reference sheet for general thickness comparison. Confirm critical specifications against project requirements before production.