

D E E C O



M E T A L S

We have a full range of foundry casting processes producing [custom castings](#). Our plants also have [extrusion](#) and [forging](#) manufacturing capabilities to supply most metal shapes or custom parts. Our standard production procedure is to always offer first article samples or prototypes, prior to beginning production of a customer's order. Our customers trust us with their critical parts because of our commitment to quality control. We are consistent in our manufacturing processes and pledge to have your custom part done right from start to finish.

METAL GAUGE TO THICKNESS CHART

Metals:		Stainless Sheet	Galvanized Steel	Standard Sheet Steel	Aluminum Sheet
Gauge	Fraction	inches (mm)	inches (mm)	inches (mm)	inches (mm)
26		0.0187 (0.452)	0.0217 (0.55)	0.0179 (0.45)	0.0159 (.40)
25		0.0219 (0.56)	0.0247 (0.63)	0.0209 (0.53)	0.0179 (0.46)
24		0.0235 (0.5969)	0.0276 (0.70)	0.0239 (0.61)	0.0201 (0.51)
23		0.0281 (0.71)	0.0306 (0.78)	0.0269 (0.68)	0.0226 (0.58)
22	1/32"	0.0293 (0.744)	0.0336 (0.85)	0.0299 (0.76)	0.0253 (0.64)
21		0.0344 (0.86)	0.0366 (0.93)	0.0329 (0.84)	0.0285 (0.71)
20		0.0355 (0.9016)	0.0396 (1.01)	0.0359 (0.91)	0.0320 (0.81)
19		0.0420 (1.067)	0.0456 (1.16)	0.0418 (1.06)	0.0359 (0.91)
18		0.0480 (1.219)	0.0516 (1.31)	0.0478 (1.21)	0.0403 (1.02)
17		0.0562 (1.4)	0.0575 (1.46)	0.0538 (1.37)	0.0453 (1.1)
16	1/16"	0.0595 (1.511)	0.0635 (1.61)	0.0598 (1.52)	0.0508 (1.29)
15		0.0703 (1.8)	0.0710 (1.80)	0.0673 (1.71)	0.0571 (1.4)
14	5/64"	0.0751 (1.9075)	0.0785 (1.99)	0.0747 (1.90)	0.0641 (1.63)
13	3/32"	0.0900 (2.286)	0.0934 (2.37)	0.0897 (2.28)	0.072 (1.8)
12	7/64"	0.1054 (2.677)	0.1084 (2.75)	0.1046 (2.66)	0.0808 (2.05)
11	1/8"	0.1200 (3.048)	0.1233 (3.13)	0.1196 (3.04)	0.0907 (2.30)
10	9/64"	0.1350 (3.429)	0.1382 (3.51)	0.1345 (3.42)	0.1019 (2.59)
9	5/32"	0.1563 (3.97)	0.1532 (3.89)	0.1495 (3.80)	0.1144 (2.91)
8	11/64"	0.165 (4.191)	0.1681 (4.27)	0.1644 (4.18)	0.1285 (3.26)
7	3/16"	0.1874 (4.76)		0.1793 (4.55)	0.1443 (3.67)
6	13/64"	0.2031		0.1943 (4.94)	0.162 (4.1)
5	7/32"	0.2187		0.2092 (5.31)	0.1819
4	15/64"	0.2344		0.2242 (5.69)	0.2043
3	1/4"	0.25		0.2391 (6.07)	0.2294